

Tecnatorch

Torch On Mineral Capsheet

Tecnatorch is a polyester reinforced SBS-modified bitumen membrane.

APPLICATION

Tecnatorch is intended for use as a torch-applied top sheet in a bitumen built-up roof system. Membranes should be installed in accordance with the manufacturer's guidelines.

| | |
|------------------------------|--|
| Upper Surface | Mineral granules with thermofusible film to overlap selvedge |
| Lower Surface | Thermofusible PE film |
| Material | SBS-Modified Bitumen |
| Type of Reinforcement | Polyester 195g/m ² |

| Characteristic | Test Method | Value or Statement | Tolerance | Units |
|--------------------------------|----------------|------------------------|-----------|-------------------|
| Length | EN 1848-1 | 8 | ±0.1 | m |
| Width (inc. Selvedge) | EN 1848-1 | 1 | ±0.02 | m |
| Mass per unit area | BS EN 1849-1 | 5 | ±0.15 | kg·m ² |
| Effective thickness | BS EN 1849-1 | 4.2 | ±0.2 | mm |
| Water tightness | BS EN 1928 (B) | Pass | - | - |
| External fire performance* | BS EN 13501-5 | B _{ROOF} (t4) | - | - |
| Tensile strength | BS EN 12311-1 | 900 (MD); 900 (TD) | ±35% | N/50 mm |
| Elongation | BS EN 12311-1 | 35 (MD); 35 (TD) | ±35% | % |
| Dimensional stability | BS EN 1107-1 | ≤ 1 | - | % |
| Flexibility at low temperature | BS EN 1109 | ≤ -15 | - | °C |
| Flow resistance at elev. temp | BS EN 1110 | > 90 | - | °C |

MD = Machine Direction. TD = Transverse Direction.

PACKAGING

| Description | Roll Dimensions | Rolls per pallet | Product Code |
|----------------------|-----------------|------------------|-----------------|
| Tecnatorch Charcoal | 8m x 1m | 25 | 10001256 |
| Tecnatorch Blue/Grey | 8m x 1m | 25 | 10001253 |
| Tecnatorch Green | 8m x 1m | 25 | 10001254 |
| Tecnatorch Brown | 8m x 1m | 25 | 10001255 |

STORAGE

Materials for reinforced bitumen membrane roofing should be stored upright on clean dry level surfaces, undercover and clear of the ground. The same protection should be given to materials temporarily kept outdoors or on the roof during construction. Storage temperatures should be between 0°C and 30°C. Refer to BS 8000-4 (Section 2.1.2.2) for further information.

INSTALLATION SUMMARY

Tecnatorch membranes are applied by torch-on application. The membrane is to be installed in accordance with current and relevant standards such as BS 8217, BS 6229 and BS 8000-4.

For further details please consult our Flat Roofing Product Installation Guidelines or contact our BMI Icopal technical services team.

TECHNICAL SERVICES

For further information and technical support, please contact our technical services team:

T: +44 (0) 330 123 4585

E: technical.uk@bmigroup.com

CERTIFICATION

Tecnatorch has been independently site and laboratory tested by the British Board of Agrément, and awarded BBA certificate number 07/4409 (PS4).



SAFETY, QUALITY & ENVIRONMENT

BMI Icopal membranes are manufactured under a Quality Management System approved to ISO 9001: 2015 and an Environmental Management System approved to ISO 14001: 2015 by TÜV NORD CERT GmbH.

Information regarding transportation, handling, storage and disposal can be found on the relevant Safety Data Sheet.



ISO 9001:2015
44 100 21410102



ISO 14001:2015
44 100 21410102



BMI Group UK Limited

BMI House, 2 Pitfield, Kiln Farm, Milton Keynes, MK11 3LW
bmigroup.com/uk

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information, suitability and specification advice, please contact BMI Icopal technical services team.