



Eurothane® GP

Eurothane GP is a thermal insulation board. Its core consists of rigid polyisocyanurate PIR foam. The board is faced with a gas diffusion tight multilayer foil on both sides. Grid pattern on both sides.

Application(s)

Thermal insulation of Pitched roofs, Framed walls, Floors (compatible with underfloor heating systems).

Board

| Description | Value | Unit | Tolerances | Standard |
|------------------------------|---|-------------------|------------|----------|
| Dimensions | | | | |
| Length | 2400 | mm | | |
| Width | 1200 | mm | | |
| Thickness range | 25 – 160 | mm | T2 | EN 823 |
| Density (core volume weight) | ± 30 | kg/m ³ | | |
| Appearance | | | | |
| Facing | Gas diffusion tight multilayer foil on both sides and grid on both sides. | | | |
| Edge finishing | Straight edges | | | |

Essential characteristics

| Description | Standard | EN code | Value | Unit |
|---|------------|-------------|-------|-------|
| Thermal conductivity (declared value) | | | | |
| All thicknesses | EN 13165 | λ_D | 0.022 | W/m.K |
| Mechanical properties | | | | |
| Compressive stress or compressive strength at 10% deformation thickness <50 mm | EN 826 | CS(10/γ)120 | ≥120 | kPa |
| Compressive stress or compressive strength at 10% deformation thickness 50-160 mm | EN 826 | CS(10/γ)140 | ≥140 | kPa |
| Fire behaviour | | | | |
| Reaction to fire (product as such) | EN 13501-1 | Euroclass | F | |

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

RECTICEL
insulation

Fire performance

BS 476
(part 7)

Class 1

Hygrometric properties

Water vapour diffusion coefficient (tabulated value)

EN ISO
10456

μ

50 - 100

(tab.
values)

Insulation Values

Thickness (mm)

λ D-value (W/mK)

RD-value (m²K/W)

| | | |
|-----|-------|------|
| 25 | 0.022 | 1.10 |
| 30 | 0.022 | 1.35 |
| 40 | 0.022 | 1.80 |
| 50 | 0.022 | 2.25 |
| 60 | 0.022 | 2.70 |
| 65 | 0.022 | 2.95 |
| 70 | 0.022 | 3.15 |
| 75 | 0.022 | 3.40 |
| 80 | 0.022 | 3.60 |
| 85 | 0.022 | 3.85 |
| 90 | 0.022 | 4.05 |
| 100 | 0.022 | 4.50 |
| 110 | 0.022 | 5.00 |
| 120 | 0.022 | 5.45 |
| 130 | 0.022 | 5.90 |
| 140 | 0.022 | 6.35 |
| 150 | 0.022 | 6.80 |
| 160 | 0.022 | 7.25 |

Standards & Certificates

Standards

Product standard

EN 13165:2012 + A2:2016

Production

ISO 9001:2015

Environmental management

ISO 14001:2015

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE



Certificates

BBA

Certificate 02/3905

(25-160mm)

Other / Miscellaneous

Production plant

Stoke-on-Trent

Enterprise Way, Whittle road, Meir park Stoke-on-Trent Staffordshire ST3 7UN

Storage/handling

The packaging in which the product is supplied, is not suitable for outside storage. Boards should be kept, dry, stored clear of the ground and covered with a weatherproof sheet, and protected from direct sunlight. Boards that have been allowed to get wet, should not be used.

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

