

## IKOpro HIGH BOND PRIMER

### PRODUCT INFORMATION

IKOpro High Bond Primer is a modified rubber water-based primer, specifically developed to prepare surfaces prior to the laying of mastic asphalt.

Pack Size	Product Code
5 Litre	23170005



### USE

IKOpro High Bond Primer is designed for use on concrete, brickwork, metal, GRP and other similar materials to prime the substrate prior to the direct installation of Mastic Asphalt

### FEATURES & BENEFITS

- Speed of Application – product is ready to use and can be applied using brushes or rollers.
- Fast drying – typically 1 hour.
- Water based
- Provides a strong bond between mastic asphalt and the substrate
- Single coat application on most surfaces

### APPEARANCE & PERFORMANCE

<b>Appearance:</b>	Orange Liquid
<b>Size:</b>	5 Litres
<b>Application Rates:</b>	Up to 5 m <sup>2</sup> /Litre (dependant on surface)
<b>Drying Time:</b>	Typically 1 Hour
<b>Shelf Life:</b>	6 Months @5-25 <sup>0</sup> C
<b>Cleaner:</b>	Soapy water when wet

### MATERIAL HANDLING

Please refer to the IKO Safety Data Sheet available from [www.ikogroup.co.uk](http://www.ikogroup.co.uk)..

### APPLICATION PRIOR TO COMMENCEMENT

Application must always follow good, safe working practice.

Prior to commencing works, it is important that operatives read the IKO Safety Data Sheet. Additionally, it is important to be aware of all the information given by employers Risk Assessments and understand all Method Statements produced for undertaking the work.

### PREPARATION

Ensure surfaces are clean, dry and free from debris, grease, fungal growth and any other contaminants. In addition, mould oil and excessive surface laitance should be removed by wire brushing or light scabbling prior to applying IKOpro High Bond Primer.

### APPLICATION

IKOpro High Bond Primer should be applied at temperatures between 5<sup>0</sup>C and 25<sup>0</sup>C.

Do not thin the material for any reason.

The primer should be applied to the prepared surface by brush or roller to give a uniform, even coating. Where necessary, a brush should be used to ensure the primer is applied fully into corners and areas of detailing.

Particularly porous surfaces may require an additional full coat of the product but be aware that over application of the product may result in longer drying times.

Drying time is typically 1 hour dependant on ambient temperature and porosity of the substrate.

## **POST COMPLETION**

The mastic asphalt should be applied as soon as practicable after the primer is dry.

If the surface of the application becomes damaged or contaminated, the surface must be swept clean and IKOpro High Bond Primer reapplied in accordance with the application section above.

Information regarding disposal of empty containers or containers with residual liquid can be found within the relevant sections of the IKO Safety Data Sheet.

## **DISCLAIMER**

Whilst every precaution is taken to ensure that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

IKO reserve the right to amend and/or withdraw this document without notice.

Intending purchasers of our materials should therefore verify with the company whether any changes in our specification, application details, withdrawals or otherwise have taken place since this literature was issued.