Profiles XL FireSmart Torch On Mineral Capsheet

Profiles XL FireSmart is a polyester reinforced SBS-modified bitumen membrane with FireSmart fire retardant.

APPLICATION

Profiles XL FireSmart is intended for use as a torch-applied top sheet in a bitumen built-up roof system. Membranes should be installed in accordance with manufacturer's guidelines.

Upper Surface	Mineral granules with thermofusible film to overlap selvedge		
Lower Surface	Thermofusible PE film		
Material	SBS-Modified Bitumen		
Type of Reinforcement	Polyester 250g/m²		

Characteristic	Test Method	Value or Statement	Tolerance	Units
Length	EN 1848-1	7	±0.1	m
Width (inc. Selvedge)	EN 1848-1	1	±0.02	m
Mass per unit area	BS EN 1849-1	5.3	±0.15	kg∙m²
Effective thickness	BS EN 1849-1	4.5	±0.2	mm
Water tightness	BS EN 1928 (B)	Pass	-	-
External fire performance*	BS EN 13501-5	B _{ROOF} (t4)	-	-
Tensile strength	BS EN 12311-1	900 (MD); 900 (TD)	±35%	N/50 mm
Elongation	BS EN 12311-1	35 (MD); 35 (TD)	±35%	%
Dimensional stability	BS EN 1107-1	≤ 1	-	%
Flexibility at low temperature	BS EN 1109	≤ -10	-	°C
Flow resistance at elev. temp	BS EN 1110	> 75	-	°C

MD = Machine Direction. TD = Transverse Direction.

BMI icopal

* The external fire performance of a roof is tested as a built-up roof system and therefore no performance can be determined from any single product alone. Please consult BMI lcopal technical services for system specific information prior to commencing construction.

PACKAGING

Description	Roll Dimensions	Rolls per pallet	Product Code
Profiles XL FireSmart Charcoal	7m x 1m	25	10001215
Profiles XL FireSmart Green*	7m x 1m	25	10001212
Profiles XL FireSmart Blue/Grey*	7m x 1m	25	10001213
Profiles XL FireSmart Brown*	7m x 1m	25	10001214

*These colours are made to order and subject to minimum order quantities and extended lead times.

STORAGE

Materials for reinforced bitumen membrane roofing should be stored upright on clean dry level surfaces, undercover and clear of the ground. The same protection should be given to materials temporarily kept outdoors or on the roof during construction. Storage temperatures should be between 0°C and 30°C. Refer to BS 8000-4 (Section 2.1.2.2) for further information.

INSTALLATION SUMMARY

Profiles XL FireSmart membranes are applied by torchon application. The membrane is to be installed in accordance with current and relevant standards such as BS 8217, BS 6229 and BS 8000-4.

For further details please consult our Flat Roofing Product Installation Guidelines or contact BMI Icopal Technical Services.

TECHNICAL SERVICES

For further information and technical support, please contact BMI Technical.

T: +44 (0) 330 123 4585 E: technical.uk@bmigroup.com

CERTIFICATION

Profiles XL FireSmart has been independently site and laboratory tested by the British Board of Agrément, and awarded BBA certificate number 07/4409 (PS1 & PS5).



SAFETY, QUALITY & ENVIRONMENT

BMI Icopal membranes manufactured under a Quality Management System approved to ISO 9001: 2015 and an Environmental Management System approved to ISO 14001: 2015, by TÜV NORD CERT GmbH.

Information regarding transportation, handling, storage and disposal can be found on the Safety Data Sheets.





BMI icopal

BMI Group UK Limited

BMI House, 2 Pitfield, Kiln Farm, Milton Keynes, MK11 3LW bmigroup.com/uk

Product, technical standards and codes of practice are under constant review. We reserve the right to change and amend products and information without prior notice. For the latest information, suitability and specification advice, please contact BMI lcopal technical services team.